CLEAR EASTAR Cover Specifications



Moniteur Devices manufacturers its Moniteur clear covers from Eastman's Eastar grade of Copolyesters. Combined with its high chemical resistance and excellent impact strength, the Ektar clear cover provides the necessary protection from corrosive environments and caustic washdowns. With an extra tough construction, the cover resists horizontal and vertical impacts. Combined with an O-ring seal, the Moniteur is an excellent opponent to the elements and your plant environment.

PHYSICAL PROPERTIES

UV Res	ista	nce	9										Yes
Clarity													Yes
Tensile	Stre	eng	jth										6,400 psi
Izod Impact Strength, Notched @73 F > 16													
Heat Deflection Temperature @264psi										151 F			

Chemical Stability @ 23 C

REAGENT OBSERVATION

Benzyl Alcohol	No Visible Effect					
Chlorox Bleach, 5% Solution	No Visible Effect					
Ethanol	No Visible Effect					
Gasoline, regular	No Visible Effect					
Heptane	No Visible Effect					
Hydraulic Fluid	No Visible Effect					
Methanol	No Visible Effect					
Methyl Cellosolve	No Visible Effect					
Methyl Isobutyl Carbinol	No Visible Effect					
Motor Oil, 10-30 Wt.	No Visible Effect					
Transmission Fluid	No Visible Effect					
20% Sulfuric Acid	No Visible Effect					
10% Sodium Hydroxide	No Visible Effect					

Eastar is a registered trademark of Eastman Chemical Chart provided courtesy of Eastman Chemical